

DUPONT™ STONETECH® PROFESSIONAL HEAVY DUTY GROUT SEALER

TECHNICAL DATA SHEET



PRODUCT BENEFITS

- Heavy duty protection against most stains
- Protects grout and makes cleaning easier
- Grout for ceramic and porcelain tile
- Preserves natural look
- Water-based formula
- Interior and exterior use

RECOMMENDED SURFACES

Grout for natural stone, ceramic and porcelain tile.

AVAILABLE SIZES

Pint, 24 oz Spray, Quart, Gallon, 5 Gallon*

COVERAGE

Up to 1,000 linear ft per gallon, depending on porosity of surface.

EXPECTED WEAR

Up to 5 years on interior surfaces and up to 3 years on exterior surfaces.

TECHNICAL INFORMATION

Form:	Liquid
Specific Gravity:	0.999
HMIS Rating:	2,0,0
Flash Point:	NA
Freeze Point:	32 °F (0 °C)
pH:	4–5

VOC CONTENT

<400 g/L (excluding water) for EPA purposes.

<120 g/L (including water) for U.S. state purposes (Low Solids Coating).

*Size not available for sale in all areas

DIRECTIONS

Read entire label before using. Use only as directed. Always test in a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Allow new grout installations to cure for at least 72 hours prior to application. Be sure surface is clean, thoroughly dry and free of waxes and coatings. Surface temperature should be between 50 °F and 80 °F (10 °C and 26.7 °C) before sealing. Ensure work area is well-ventilated during application and until surface is dry. Keep children and pets out of the area until treated surface is dry.

1. Apply directly onto grout lines and joints to thoroughly wet surface using a paint pad, roller or brush. Avoid applying sealer on unintended surfaces.
2. Allow sealer to completely penetrate into the grout, 5–15 minutes.
3. Liberally apply a second coat following steps 1–2.
4. Wipe up all sealer from the surface of the tile. Use a clean, dry, lint-free, cotton towel or mop to remove excess sealer.
5. If sealer was not completely wiped off and a residue appears, wipe entire surface with a towel dampened with sealer. Use a white nylon pad to loosen residue and follow with a clean, white absorbent towel to remove.
6. A full cure is achieved after 24–48 hours; foot traffic may begin in 4 hours. If needed sooner, cover the floor with red resin paper to protect it until full cure is achieved.
7. Clean tools used during application with water.

STORAGE AND HANDLING INSTRUCTIONS

CAUTION: MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE, SKIN AND RESPIRATORY IRRITATION. Do not ingest. Avoid contact with eyes and skin. Avoid prolonged exposure to vapors. KEEP OUT OF THE REACH OF CHILDREN. Do not freeze or store above 100 °F/38 °C. Do not mix with other chemicals. Do not release to natural waterways.

EMERGENCY/FIRST AID PROCEDURES

Ingestion: Do not induce vomiting. Call poison control center. Call a physician.

Eye Contact: Flush thoroughly with water for at least 15 minutes. Call a physician if eye irritation persists.

Skin Contact: Wash skin with mild soap and water. Call a physician if skin irritation persists. Launder affected clothing before re-wearing.

Inhalation: Remove affected person to fresh air. Call a physician if respiratory irritation persists.

The DuPont™ StoneTech® Professional product line complies with all federal, state and local VOC regulatory requirements and is packaged in containers with at least 25% post-consumer recycled material.

PROTECT

CLEAN

TRANSFORM

DuPont™ StoneTech® Professional
2520 Barrington Court
Hayward, CA 94545

Technical Support: 888-786-6343
Customer Service: 877-786-6383

www.stonetechpro.com



The miracles of science™

The information is furnished free of charge and based on information that DuPont believes to be generally reliable and accurate. Individual facts and circumstances may differ. It is intended for your use at your own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.

Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and StoneTech® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

K-20506-2 (03/14)